



Antistatic polyurethane hose, light, microbe resistant + flame-retardant

**Applications**

- flexible hose/ ducting for gases and for abrasive dust, powder, fibres
- printed circuit board drilling machine (PCB)
- extraction unit, dedusting system, filter system, oil mist extraction
- extraction arm
- chemical industry: chemical vapours, vapour return hose at loading arm, paint steam, spray mist extraction
- explosion hazard area
- textile industry, fiber extraction: spinning machine, knitting machine, weaving loom machine
- animal stall, animal shed: barn ventilation
- clean room ventilation, semiconductor production machine
- surface preparation: shot blasting/ sand blasting recovery e.g. at blasting chamber, ship yard, stripping machine, flooring preparation machine, grinding machine
- heating hose: exterior hose as protection hose

**Properties**

- lightweight and reinforced
- highly flexible + compressible 3:1
- abrasion-resistant
- microbe resistant
- good resistance to oil, gasoline and chemicals
- very good low temperature flexibility
- flame-retardant according to: UL94-HB
- flame-retardant according to: DIN 4102-B1
- permanently antistatic wall: in accordance with ISO 8031 electrical and surface resistance <math><10^9 \Omega</math>
- in accordance with ATEX 2014/34/EU (1999/92/EC) and German TRGS 727: aspiration of combustible dust (zone 22 inside), for conveying of non-flammable liquids, for use in zone 1 and 2 (gases)
- conforms to the safety regulations of the German Wood Trade Association
- conforms to RoHS guideline

**Temperature Range**

- 40°C to 90°C
- short time to 125°C

**Design, Material**

patented PROTAPE® tape hose

- spring steel wire integrated in wall
- wall: permanently antistatic premium ester-polyurethane (Pre-PUR®)
- wall thickness 0,6 mm approx.

**Delivery variants**

- further diameters and lengths available on request
- transparent (standard)
- special colours: partially coloured, completely coloured
- customer-specific branding

I.D. in / mm	O.D. mm	Pressure DIN 26057 (50% Elongation) bar	Vacuum DIN 26057 (axially fixed) bar	Bending Radius mm	Weight kg/m	Dimensions in Stock m	Order No.
1 / 25	32	1,605 (4,18)	0,540 (1,00)	20	0,15	5 10 15	330-0025-1002
- / 30	37	1,350 (3,50)	0,450 (1,00)	22	0,18	5 10 15	330-0030-1002
1,25 / 32	39	1,265 (3,29)	0,420 (1,00)	23	0,19	5 10 15	330-0032-1002
1,5 / 38	45	1,075 (2,78)	0,355 (0,77)	26	0,22	5 10 15	330-0038-1002
- / 40	47	1,020 (2,64)	0,335 (0,69)	27	0,23	5 10 15	330-0040-1002
2 / 50-51	58	0,820 (2,12)	0,220 (0,87)	33	0,37	5 10 15	330-0050-1002
2,36 / 60	68	0,685 (1,77)	0,180 (0,61)	38	0,43	5 10 15	330-0060-1002
2,5 / 63-65	73	0,635 (1,64)	0,165 (0,52)	41	0,46	5 10 15	330-0065-1002
- / 70	78	0,590 (1,52)	0,155 (0,45)	43	0,5	5 10 15	330-0070-1002
3 / 75-76	83	0,550 (1,42)	0,145 (0,40)	46	0,53	5 10 15	330-0075-1002
- / 80	88	0,515 (1,33)	0,135 (0,35)	48	0,57	5 10 15	330-0080-1002
3,5 / 89-90	98	0,460 (1,19)	0,120 (0,28)	53	0,63	5 10 15	330-0090-1002
4 / 100-102	108	0,415 (1,07)	0,080 (0,31)	58	0,67	5 10 15	330-0100-1002
- / 110	118	0,375 (0,97)	0,070 (0,26)	63	0,73	5 10 15	330-0110-1002
4,5 / 114-115	123	0,360 (0,93)	0,070 (0,24)	66	0,76	5 10 15	330-0115-1002
4,72 / 120	128	0,345 (0,89)	0,065 (0,22)	68	0,79	5 10 15	330-0120-1002
5 / 125-127	133	0,335 (0,86)	0,065 (0,20)	71	0,83	5 10 15	330-0125-1002
- / 130	138	0,320 (0,82)	0,060 (0,19)	73	0,86	5 10 15	330-0130-1002
5,5 / 140	148	0,295 (0,76)	0,055 (0,16)	78	0,92	5 10 15	330-0140-1002
6 / 150-152	158	0,275 (0,71)	0,055 (0,14)	83	0,99	5 10 15	330-0150-1002
6,3 / 160	168	0,260 (0,67)	0,050 (0,12)	88	1,05	5 10 15	330-0160-1002
- / 170	178	0,245 (0,63)	0,045 (0,11)	93	1,11	5 10 15	330-0170-1002

Overpressure and underpressure are recommended threshold operating values, products can be subjected to higher loads upon request. The bending radius is measured through the inside of the hose arch. Additional technical data at [www.norres.com](http://www.norres.com). The right to make technical modifications is reserved. All values determined at 20°C and are approx. data.



I.D. in / mm	O.D. mm	Pressure DIN 26057 (50% Elongation) bar	Vacuum DIN 26057 (axially fixed) bar	Bending Radius mm	Weight kg/m	Dimensions in Stock m	Order No.
- / 175	183	0,240 (0,61)	0,045 (0,10)	96	1,14	5 10 15	330-0175-1002
7 / 178-180	188	0,230 (0,59)	0,045 (0,10)	98	1,17	5 10 15	330-0180-1002
8 / 200-203	208	0,210 (0,54)	0,030 (0,11)	108	1,33	5 10 15	330-0200-1002
- / 225	233	0,185 (0,48)	0,025 (0,09)	121	1,48	5 10	330-0225-1002
- / 250	258	0,165 (0,43)	0,025 (0,07)	133	1,64	5 10	330-0250-1002
10 / 254	262	0,165 (0,42)	0,025 (0,06)	135	1,66	5 10	330-0254-1002
11 / 280	288	0,150 (0,38)	0,020 (0,05)	148	1,83	5 10	330-0280-1002
- / 300	309	0,140 (0,36)	0,020 (0,05)	159	2,14	5 10	330-0300-1002
12 / 305	314	0,135 (0,35)	0,020 (0,05)	162	2,17	5 10	330-0305-1002
- / 315	324	0,135 (0,34)	0,020 (0,05)	167	2,24	5 10	330-0315-1002
- / 350	359	0,120 (0,31)	0,020 (0,04)	184	2,49	5 10	330-0350-1002
14 / 356	365	0,115 (0,30)	0,015 (0,03)	187	2,53	5 10	330-0356-1002
- / 400	409	0,105 (0,27)	0,015 (0,02)	209	2,84	5 10	330-0400-1002
- / 450	459	0,095 (0,24)	0,015 (0,02)	234	3,19	5 10	330-0450-1002
- / 500	510	0,085 (0,21)	0,015 (0,02)	260	4,39	5 10	330-0500-1002

Overpressure and underpressure are recommended threshold operating values, products can be subjected to higher loads upon request. The bending radius is measured through the inside of the hose arch. The right to make technical modifications is reserved. All values determined at 20°C and are approx. data. Additional technical data at [www.norres.com/en/technology/](http://www.norres.com/en/technology/)